


CERIA STABILIZED ZIRCONIA (CSZ)

Consider CSZ a top candidate when choosing a material for high strength and toughness in moist, challenging environments. With high flexural strength and very high compressive strength this material is ideally suited as a structural component in sensors, instrumentation, probes, pumps and fluid control systems.



PRIME FEATURES

CSZ offers a more robust Stabilized Zirconia material when low temperature degradation properties are in question, displaying a reduced vulnerability of molecular water attack compared to YTZP or MSZ. The ability of this material to withstand high temperature, wet operating conditions elevates its performance above other ceramic materials.

TYPICAL APPLICATIONS

- Instrumentation
- Sensors
- Seals
- Bearings
- Desalination plant components
- Steam system instrumentation
- Boiler probes
- Underwater sensors
- Medical instrumentation
- Pump pistons
- Pump liners
- Valve seats
- Emission sensors
- Marine system components
- Chemical pumps
- Fluid metering pumps
- Fluid control valves
- Chemical analysis fluid control systems

Superior Technical Ceramics products and services are subject to the Company's standard terms and conditions, available on request or at ceramics.net. For more information contact an authorized Superior Technical Ceramics representative. Unless noted otherwise, trademarks and service marks herein are the property of Superior Technical Ceramics and may be registered in the United States and/or other countries. Superior Technical Ceramics products named herein may be protected by one or more U.S. and/or foreign patents. For more information, contact sales@ceramics.net. Specifications are subject to change without notice. Superior Technical Ceramics sells its products and services in accordance with the terms and conditions set forth in the applicable contract between Superior Technical Ceramics and the client.



CERIA STABILIZED ZIRCONIA SPECIFICATIONS

	Property	ASTM Method	Units	CSZ (Ceria Stabilized)
General	Crystal Size (Average)	Thin Section	Microns	3
	Color	--	--	Yellow
	Gas Permeability	--	atms-cc/sec	gas tight <10 ⁻¹⁰
	Water Absorption	C 20-97	%	0
Mechanical	Density	C 20-97	g/cc	6.20
	Hardness	Vickers 500 gm	GPa (kg/mm ²)	11.7 (1200)
	Hardness	--	R45N	78
	Fracture Toughness	Notched Beam	MPam ^{1/2}	12
	Flexural Strength (MOR) (3 point) @ RT°	F417-87	MPa (psi x 10 ³)	551 (80)
	Tensile Strength @ RT°	--	MPa (psi x 10 ³)	337 (49)
	Compressive Strength @ RT°	--	MPa (psi x 10 ³)	2000 (290)
	Elastic Modulus	C848	GPa (psi x 10 ⁶)	200 (29)
Poisson's Ratio	C848	--	0.25	
Thermal	C.T.E. 25 - 100° C	C 372-96	x 10 ⁻⁶ /C	6.9
	C.T.E. 25 - 300° C	C 372-96	x 10 ⁻⁶ /C	8.1
	C.T.E. 25 - 600° C	C 372-96	x 10 ⁻⁶ /C	10.5
	Thermal Conductivity @ RT°	C 408	W/m K	3.5
	Max Use Temp (non-loading) (at high strength)	--	Fahrenheit (°F)	1000
	--	Celcius (°C)	537	
Electrical	Dielectric Strength (.125" Thick)	D 149-97A	V/mil	250
	Dielectric Constant @ 1 MHz	D 150-98	--	30.0
	Dielectric Constant @ Gigahertz	D 2520-95	--	--
	Dielectric Loss @ 1 MHz	D 150-98	--	0.0010
	Dielectric Loss @ Gigahertz	D 2520-95	--	--
	Volume Resistivity, 25° C	D 257	ohms-cm	> 1 x 10 ¹³
	Volume Resistivity, 300° C	D 1829	ohms-cm	1 x 10 ¹⁰
	Volume Resistivity, 500° C	D 1829	ohms-cm	1 x 10 ⁶
	Volume Resistivity, 700° C	D 1829	ohms-cm	5 x 10 ³
	Volume Resistivity, 1000° C	D 1829	ohms-cm	--

Form Revised: 8/12/2014

CONTACT US

Superior Technical Ceramics | 600 Industrial Park Rd. | St. Albans, VT 05478 | www.ceramics.net
 Telephone: (802) 527-7726 | Fax: (802) 527-1181 | Email: sales@ceramics.net