

## Zirconia Ceramic Materials

---

Yttria Stabilized Zirconia (YTZP)

Magnesia Stabilized Zirconia (MSZ)

Ceria Stabilized Zirconia (CSZ)

Zirconia Toughened Alumina (ZTA)

---

### Contact us:

---

STC looks forward to working closely with you on your quest for a ceramic material solution to any challenging application you may have. We are certain that you will find STC's full service staff an ideal partner to undertake your ceramic component projects.

<b>Telephone</b>	(802) 527-7726
<b>Fax</b>	(802) 527-1181
<b>Email</b>	<a href="mailto:sales@ceramics.net">sales@ceramics.net</a>




**Superior Technical Ceramics**  
*Engineering. Partnership. Solutions.*

---

600 INDUSTRIAL PARK RD. ST. ALBANS, VT 05478  
[WWW.CERAMICS.NET](http://WWW.CERAMICS.NET)

---

Revised 01/05/2021



Electron Microscope image of YTZP



Electron Microscopic image of MSZ

## Zirconia Ceramics

---

Stabilized Zirconia's are among the strongest ceramic materials we offer. Each one offers different specific properties that can be applied to meet the demands of extreme applications across many industries. Offering very high strength, high toughness, wear/abrasion resistance, and corrosion resistance they can be used in operating environments that plastics, metals and other ceramic materials cannot withstand. Visit our website to review the properties of each material and call us to discuss if they are the solution you are looking for.

## Properties

---

Our understanding of materials helps us guide you through the selection process:

- High strength, hardness & fracture toughness
- Non-magnetic & wear resistant
- Good frictional behaviour
- Electrical insulation
- Low thermal conductivity
- Corrosion resistance in acids and alkalis
- Modulus of elasticity similar to steel
- Coefficient of thermal expansion similar to iron.



## Ceramic Engineering Insight

---

Our 117 years of ceramics engineering experience allows us to provide guidance in material selection, design-to-manufacture geometry and cost effective production.



## Total Process Control

---

How do we control quality? By controlling every aspect of manufacturing in-house, from raw material through to finished component. All aspects of our manufacturing processes are governed by the same principles of total quality management, including powder preparation, forming, green machining, sintering and diamond grinding.



## Customer Service Focus

---

In the larger world of ceramics, we're a mid-sized firm located in Vermont. We pride ourselves on providing direct access to our key team members and quick response times for our customers.

**Call** (802) 527-7726

**E-mail** [sales@ceramics.net](mailto:sales@ceramics.net)

YTNP

- 

- 

- # ANTA

- 
- A collection of various white plastic components, likely for automotive or industrial use, arranged on a black background. The items include a large circular ring, a tall cylindrical container, a smaller cylindrical container, a rectangular block, a small square component with a circular opening, a small cylindrical cap, a long thin rod, and a small rectangular component with a circular opening.

# Materials Property Chart

				Zirconia					Zirconia Toughened Alumina		
	Property	ASTM Method	Units	MSZ (Magnesia Stabilized) MSZ-200	MSZ (Magnesia Stabilized) MSZ-300	YTZP 2000 (Yttria Stabilized)	YTZP 4000 (Yttria Stabilized)	CSZ (Ceria Stabilized)	ZTA-02 US Patent 8679995	ZTA-14	ZTA-20
General	Crystal Size (Average)	Thin Section	Microns	30	30	1	1	3	< 2	6	3
	Color	--	--	Ivory	Yellow	Ivory	Ivory	Yellow	Off White	White	White
	Gas Permeability	--	atms-cc/sec	gas tight <10 <sup>-10</sup>	gas tight <10 <sup>-10</sup>	gas tight <10 <sup>-10</sup>	gas tight <10 <sup>-10</sup>	gas tight <10 <sup>-10</sup>	gas tight <10 <sup>-10</sup>	gas tight <10 <sup>-10</sup>	gas tight <10 <sup>-10</sup>
	Water Absorption	C 20-97	%	0	0	0	0	0	0	0	0
Mechanical	Density	C 20-97	g/cc	5.72	5.72	6.02	6.07	6.20	3.96	4.17	4.30
	Hardness	Vickers 500 gm	GPa (kg/mm²)	11.7 (1200)	11.7 (1200)	12.5 (1250)	12.5 (1250)	11.7 (1200)	14 (1440)	14.5 (1478)	14.4 (1470)
	Hardness	--	R45N	78	78	80	80	78	81	82	82
	Fracture Toughness	Notched Beam	MPam <sup>1/2</sup>	12	12	10	10	12	5	6	6
	Flexural Strength (MOR) (3 point) @ RT°	F417-87	MPa (psi x 10³)	620 (90)	586 (85)	951 (138)	1380 (200)	551 (80)	448 (65)	586 (85)	621 (90)
	Tensile Strength @ RT°	--	MPa (psi x 10³)	310 (45)	310 (45)	550 (80)	690 (100)	337 (49)	259 (38)	344 (50)	350 (51)
	Compressive Strength @ RT°	--	MPa (psi x 10³)	1862 (270)	1862 (270)	2485 (360)	2485 (360)	2000 (290)	2413 (350)	2758 (400)	2758 (400)
	Elastic Modulus	C848	GPa (psi x 10⁵)	206 (29.8)	206 (29.8)	210 (30)	210 (30)	200 (29)	358 (52)	338 (49)	338 (49)
Poisson's Ratio	C848	--	0.28	0.28	0.30	0.30	0.25	0.23	0.23	0.23	
Thermal	C.T.E. 25 - 100° C	C 372-96	x 10 <sup>-6</sup> /C	8.9	8.9	6.9	6.9	6.9	6.7	6.0	6.0
	C.T.E. 25 - 300° C	C 372-96	x 10 <sup>-6</sup> /C	9.7	9.7	8.1	8.1	8.1	8.1	7.0	7.0
	C.T.E. 25 - 600° C	C 372-96	x 10 <sup>-6</sup> /C	10.0	10.0	10.5	10.5	10.5	8.3	7.1	7.1
	Thermal Conductivity @ RT°	C 408	W/m K	3	3	2.2	2.2	3.5	27	24	24
	Max Use Temp (non-loading) (at high strength)	--	Fahrenheit (°F)	2200	2200	932	932	1000	2732	2730	2730
		--	Celsius (°C)	1200	1200	500	500	537	1500	1500	1500
Electrical	Dielectric Strength (.125" Thick)	D 149-97A	V/mil	300	300	240	240	250	230	250	250
	Dielectric Constant @ 1 MHz	D 150-98	--	22.7	22.7	30.0	30.0	30.0	10.5	12.5	12.5
	Dielectric Constant @ Gigahertz	D 2520-95	--	29.2	29.2	--	--	--	--	--	12.4
				6.2	6.2	--	--	--	--	9.4	
	Dielectric Loss @ 1 MHz	D 150-98	--	0.0016	0.0016	0.0010	0.0010	0.0010	0.0003	0.0006	0.0006
	Dielectric Loss @ Gigahertz	D 2520-95	--	0.0018	0.0018	--	--	--	--	0.0005	0.0005
				6.2	6.2	--	--	--	--	9.4	9.4
	Volume Resistivity, 25°C	D 257	ohms-cm	> 1 x 10 <sup>13</sup>	> 1 x 10 <sup>13</sup>	> 1 x 10 <sup>13</sup>	> 1 x 10 <sup>13</sup>	> 1 x 10 <sup>13</sup>	> 1 x 10 <sup>14</sup>	> 1 x 10 <sup>14</sup>	> 1 x 10 <sup>14</sup>
	Volume Resistivity, 300° C	D 1829	ohms-cm	5 x 10 <sup>7</sup>	5 x 10 <sup>7</sup>	1 x 10 <sup>10</sup>	1 x 10 <sup>10</sup>	1 x 10 <sup>10</sup>	3 x 10 <sup>12</sup>	1 x 10 <sup>10</sup>	1 x 10 <sup>10</sup>
	Volume Resistivity, 500° C	D 1829	ohms-cm	1 x 10 <sup>7</sup>	1 x 10 <sup>7</sup>	1 x 10 <sup>8</sup>	1 x 10 <sup>8</sup>	1 x 10 <sup>8</sup>	6 x 10 <sup>10</sup>	2 x 10 <sup>9</sup>	2 x 10 <sup>9</sup>
	Volume Resistivity, 700° C	D 1829	ohms-cm	2 x 10 <sup>6</sup>	2 x 10 <sup>6</sup>	5 x 10 <sup>3</sup>	5 x 10 <sup>3</sup>	5 x 10 <sup>3</sup>	6 x 10 <sup>9</sup>	2 x 10 <sup>8</sup>	4 x 10 <sup>8</sup>
Volume Resistivity, 1000° C	D 1829	ohms-cm	--	--	--	--	--	--	--	--	

Note: The information in this data sheet is for design guidance only. STC does not warrant this data as absolute values. Forming methods and specific geometry could affect properties. Slight adjustments can be made to some of the properties to accommodate specific customer...

...requirements. Most of the dense materials in the table are resistant to mechanical erosion and chemical attack. STC has performed ASTM testing qualification for certain compositions, in accordance with ASTM D2442. Please consult our technical staff for appropriate material and specific test results.

USA OWNED &  
OPERATED



ITAR  
REGISTERED



AS9100 &  
ISO 9001



DFARS  
CYBER COMPLIANT



REACH  
COMPLIANT



RoHS  
COMPLIANT



For a complete version of the  
Materials Property Chart, visit [ceramics.net](http://ceramics.net)